

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
22 November 2001 (22.11.2001)

PCT

(10) International Publication Number
WO 01/87636 A1

(51) International Patent Classification⁷: **B41M 7/00, 5/00**

Manfred [DE/DE]; Biebererstr.46, 63165 Muehlheim (DE). **STRUEWE, Volker** [DE/DE]; Barbarossastr.119, 63128 Dietzenbach (DE).

(21) International Application Number: PCT/US01/14162

(22) International Filing Date: 2 May 2001 (02.05.2001)

(74) Agent: **SINNOTT, Jessica, M.**; E.I. Du Pont de Nemours and Company, Legal Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).

(25) Filing Language: English

(26) Publication Language: English

(81) Designated State (*national*): US.

(30) Priority Data:
EP 00110550.1 17 May 2000 (17.05.2000) DE

(84) Designated States (*regional*): European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR).

(71) Applicant (*for all designated States except US*): **E. I. DU PONT DE NEMOURS AND COMPANY** [US/US]; 1007 Market Street, Wilmington, DE 19898 (US).

Published:
— with international search report

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **SONDERGELD,**

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 01/87636 A1

(54) Title: **INK RECEPTOR SHEET AND ITS PROCESS OF USE**

(57) Abstract: The present invention is directed to an ink receptor sheet for ink jet printing, an ink jet printing system comprising such an ink receptor sheet and a transfer element, a process for preparing an image on a permanent support by ink jet printing, and an imaged article made by such a process. By incorporation of a photopolymerizable layer into an ink receptor sheet, the handling latitude during lamination and peeling steps of ink jet printing processes was enhanced and/or more durable and resistant images made by such ink jet printing processes were provided.

TITLE

INK RECEPTOR SHEET AND ITS PROCESS OF USE

FIELD OF INVENTION

The invention relates to an ink receptor sheet, a printing system
5 comprising such an ink receptor sheet and a transfer element, a process for
preparing an image on a permanent substrate by formation of an ink image, and
an imaged article made by such a process.

BACKGROUND OF INVENTION

Ink jet printing is a well known process in the art to make multicolor
10 images. It is a non-impact method for recording information in response to an
electronic signal, such as that generated by a computer. In this process, ink
droplets are emitted from a nozzle and deposited on substrates, mainly paper or
polymer films and sheets, to form an ink image. To achieve high quality images
in ink jet printing, the substrate is usually coated with at least one layer that
15 rapidly absorbs the ink. For the inks are mainly composed of water and a
colorant, such coating formulations are hydrophilic and contain appropriate
absorptive materials.

It is also possible to transfer the ink image present on the ink receiving
layer of an ink receiving sheet, comprising a temporary support and an ink
20 receiving layer, to a permanent substrate. After peeling of the temporary support,
the image is transferred to the permanent substrate.

Alternatively, the imaged ink receptor sheet may first be laminated to a
transfer element. Then the temporary support of the ink receptor sheet is
removed, the imaged ink receiving layer on the transfer element is then laminated
25 to the desired permanent substrate, and finally the transfer element is removed.

Ink jet printing materials and transfer processes are known from
US 5,023,129, US 5,141,797, and US 5,984,467. Ink receptor sheets which
provide ink images with improved durability are known from US 5,429,860 and
US 5,537,137. These materials contain special compounds in the ink receiving
30 layer which compounds are crosslinked by heat, by actinic radiation, or by
chemical treatment after ink jet printing. Another method to provide durable ink
jet images is disclosed in US 5,766,398. This method provides images with a
protective layer on the ink image by using an ink receptor sheet comprising a
temporary support, a polymeric film, and an ink receiving layer. After applying
35 an image by ink jet printing to the ink receiving layer, a substrate comprising an
adhesive layer is laminated to the imaged ink receptor sheet, and the temporary
support of the ink receptor sheet is removed, whereby the polymeric film is
revealed as a protective layer of the ink image.

There are still problems with the ink jet materials and processes of the prior art, such as they often have narrow handling latitude during the required lamination and peeling steps. Either high lamination temperatures and slow lamination speeds are necessary or it is difficult to separate the right layers in the peeling steps to get the desired end result.

SUMMARY OF INVENTION

Therefore, it was an objective of the present invention to enhance the handling latitude during the required lamination and peeling steps of ink jet printing processes and/or to provide durable and resistant images made by such ink jet printing processes.

In a first aspect, this objective is achieved by an ink receptor sheet comprising a first temporary support and an ink receiving layer, characterized in that it additionally comprises a photopolymerizable layer between the first temporary support and the ink receiving layer.

In a second aspect, the invention is directed to an ink jet printing system comprising in combination an ink receptor sheet and a transfer element comprising a second temporary support and an adhesive layer.

In a third aspect, the invention is directed to a process for preparing an image on a permanent substrate comprising the steps of:

- (a) imagewise applying at least one ink image on an ink receptor sheet, wherein the ink receptor sheet comprises, in order:
 - (1) a first temporary support,
 - (2) a photopolymerizable layer,
 - (3) and an ink receiving layer, and whereby the ink image is adjacent the ink receiving layer;
- (b) contacting, typically laminating, the imaged ink receptor sheet to a transfer element comprising:
 - (I) a second temporary support,
 - (II) and an adhesive layer, whereby the ink image is adjacent the adhesive layer;
- (c) removing the second temporary support to reveal the adhesive layer on top of the imaged ink receptor sheet,
- (d) contacting, typically laminating, the imaged ink receptor sheet with a permanent substrate, whereby the adhesive layer is adjacent the permanent substrate,
- (e) overall exposing with actinic radiation the permanent substrate and imaged ink receptor sheet sandwich through the first temporary support, and

- (f) removing the first temporary support to reveal the final image on the permanent substrate, wherein the image is encased between the ink receiving layer and the adhesive layer. Typically an ink jet printer is used for the imagewise application of the image.

5 In a fourth aspect, the invention is directed to an imaged article comprising a permanent substrate, an adhesive layer, an image, typically an ink jet image, an ink receiving layer, and a photopolymerized layer.

DETAILED DESCRIPTION OF INVENTION

The present invention provides an ink receptor sheet which enhances the
10 handling latitude during the required contacting, typically lamination, and peeling steps of ink jet printing transfer processes. It is not necessary to use special coated or treated synthetic resin films as temporary supports for the ink receptor sheet. No adhesion failure occurs during the peeling processes of temporary supports, even with non-pretreated temporary supports. Therefore, no edge lifting of layers
15 or partial peel off of layer surfaces damaging the final images results. Furthermore, the present invention provides durable and resistant images made by such ink jet printing processes, and simultaneously provides a protective layer for the final images.

Ink receptor sheet

20 The ink receptor sheet comprises a temporary support, a photopolymerizable layer, and an ink receiving layer.

Temporary support:

Suitable supports are, for example, synthetic resin films of polyethylene, polypropylene, polyamides, or polyesters. Polyethylene terephthalate films are
25 particularly preferred. Supports having smooth or rough surfaces can be used. Support films having release layers or surfaces treated by electrical discharge are also suitable. The thickness of the support is usually at least about 12 μm , typically about 20-200 μm , more typically about 75-150 μm .

Photopolymerizable layer:

30 Preferably, the photopolymerizable layer in its non-photopolymerized state shows high adhesion to the ink receiving layer and the first temporary support, whereas the photopolymerizable layer in its photopolymerized state shows high adhesion to the ink receiving layer and low adhesion to the first temporary support.

35 The photopolymerizable layer comprises at least one polymeric binder, at least one photopolymerizable, ethylenically unsaturated monomer, and at least one photoinitiator or photoinitiator system.

Especially, the photopolymerizable layer comprises at least one polymer selected from the group consisting of polyvinylformal, polyvinyl butyral, polyvinyl alcohol, polyvinyl acetate, polyurethane esters, polyacrylates containing carboxylic groups, polymethacrylates, and copolymers of (meth)acrylic acid with (meth)acrylic esters, (meth)acrylic amides, vinyl compounds, styrene, and butadiene. Preferred are polyvinyl alcohols and copolymers of alkyl methacrylates, e.i. methyl methacrylate, ethyl methacrylate, butyl methacrylate, and alkyl acrylates, e.i. methyl acrylate, ethyl acrylate, butyl acrylate. Especially mixtures of such polymers are suitable. For aqueous coating solutions polymer latices are used. Also suitable are the crosslinked polymers disclosed in US 4,892,802.

Conventional photopolymerizable, ethylenically unsaturated monomers may be used in the ink receptor sheets of this invention. Especially those disclosed in US 4,892,802 are typical. Typically used are acrylic and methacrylic acid esters of polyols, such as, diethylene glycol diacrylate, 1,3-propanediol dimethacrylate, 1,5-pentanediol dimethacrylate, trimethylol propane trimethacrylate, bisacrylates or methacrylates of bisphenol A or its alkoxylated derivatives, and pentaerythritol tetraacrylate or methacrylates. More typically, the photopolymerizable layer comprises at least one monomer selected from the group consisting of trimethylol propane trimethacrylate, bisacrylates or methacrylates of bisphenol A, and pentaerythritol tetraacrylate or methacrylates.

As a photoinitiator or photoinitiator system, practically all compounds known for this purpose can be used. Typically compounds and systems are disclosed in US 4,892,802. Especially preferred are diacetyl, benzil, benzil dimethyl ketal, benzoin, benzoin methyl or ethyl ether, a combination of Michler's ketone and benzophenone, and systems of substituted thioxanthenes and tertiary amines.

In addition to the main components described in the foregoing, the photopolymerizable layer of the present invention may comprise conventional additives like, for example, UV absorbers, thermal stabilizers, plasticizers, and fillers. In particular, the addition of fillers, such as, for example, silicates, aluminium oxides, and silicon dioxides are advantageous. Pyrogenic and precipitated silicic acids are preferred. Fillers are present in an amount of from about 0 to about 15 % by weight, typically 0 to 10 % by weight, based on the total weight of the layer.

The photopolymerizable layer of the invention generally comprises about 25 to about 75 % by weight, typically about 35 to about 50 % by weight of the polymeric binder; about 10 to about 60 % by weight, typically about 15 to about

50 % by weight of the photopolymerizable, ethylenically unsaturated monomer; about 0.1 to 10 % by weight, typically about 1 to about 5 % by weight of the photoinitiator or photoinitiator system; and about 0 to about 10 % by weight, typically about 1 to about 10 % by weight of additives; based on the total weight of the photopolymerizable layer.

The photopolymerizable layer of this invention can be prepared by generally known coating methods. For this purpose, aqueous as well as organic coating solutions can be used, as, for example, methylene chloride, toluene/methanol mixtures, or other mixtures of aromatic solvents and alcohols, esters, or ketones. Preferably, the photopolymerizable layer is made by emulsion coating. Subsequently, the coated layer is dried. The coating weight of the photopolymerizable layer is about 25 to about 80 mg/dm², typically about 40 to about 60 mg/dm².

Ink receiving layer

In general, all ink receiving materials of the state of the art, including those which are composed of at least two layers, can be used for preparing the ink receiving layer of this invention. Suitable ink receiving materials are described in US 5,023,129, US 5,141,797, US 5,984,467, US 5,429,860 and US 5,537,137. Preferably, the ink receiving layers of the present invention are non-tacky. The ink receiving layer of the present invention typically comprises at least one hydrophilic polymer. More typically, the ink receiving layer comprises at least one polymer selected from the group consisting of homo- and copolymers of vinyl alcohol and/or pyrrolidone; homo- and copolymers of acrylic acid, methacrylic acid, and/or maleic acid and /or maleic acid anhydride, and/or their metal salts and/or their amine salts; gelatine, and starch. Especially mixtures of polyvinyl alcohols and/or copolymers of maleic acid or maleic acid anhydride with comonomers like methyl vinyl ether, are used. The hydrophilic polymer generally will be water-soluble in order that it may be applied using conventional aqueous coating techniques.

Additional compounds of the ink receiving layer may be, for example, UV absorbers, coating additives, plasticizers, and fillers. When polymers comprising acid groups are used, preferably compounds which neutralize these acid groups are added to adjust the pH value. Typically, amines are used; especially tertiary amines like triethanol amine, are used. In particular, the addition of fillers, such as, for example, silicates, aluminium oxides, and silicon dioxides is advantageous. Pyrogenic and precipitated silicic acids are preferred. Fillers are present in an amount of from about 0 to about 15 % by weight, typically about 0 to about 10 % by weight, based on the total weight of the layer.

The ink receiving layer of this invention can be prepared by generally known coating methods. Subsequently, the coated layer is dried. The coating weight of the ink receiving layer is about 50 to about 150, typically about 60 to about 100 mg/dm².

5 Transfer element

The transfer element of the present invention comprises a temporary support and an adhesive layer. Suitable supports are, for example, synthetic resin films of polyethylene, polypropylene, polyamides, or polyesters. Polyethylene terephthalate films particularly preferred. Supports having smooth or rough
10 surfaces can be used. Support films having release layers or surfaces treated by electrical discharge are also suitable. The thickness of the support is usually at least about 12 µm, typically about 20-about 130 µm, more typically at about 50 to about 100 µm.

The adhesive layer may comprise at least one thermoplastic polymer, for
15 example at least one polymer selected from the group consisting of acrylate and methacrylate copolymers, vinyl acetate copolymers, and polyamides. Preferably the adhesive layer of the transfer element comprises at least one crystalline polymer. Especially preferred are polycaprolactones. The adhesive layer can also contain additives, such as, for example, surfactants and fillers. In particular,
20 addition of fillers, such as, for example, silicates, aluminium oxides, and silicon dioxides are advantageous. Pyrogenic and precipitated silicic acids are preferred. Fillers are present in an amount of from about 0 to about 15 % by weight, typically about 0 to about 10 % by weight, based on the total weight of the layer.

The transfer element of this invention can be prepared by known
25 methods. For this purpose, coating solutions for forming the adhesive layer can be coated on the supports from currently available solvents, preferably organic solvents, such as, for example, methylene chloride, toluene/methanol mixtures, or other mixtures of aromatic solvents and alcohols, esters, or ketones and subsequently dried. The coating weight of the adhesive layer is
30 about 30 to about 100 mg/dm², typically about 40 to about 80 mg/dm².

Inks

The inks used in the ink jet printing process of the present invention are well known in the art. The ink compositions usually comprise a carrier medium, normally water, and a colorant, which may be a dye or a pigment dispersion.
35 Furthermore, additives like detergents, thickeners, organic solvents, etc. may be present. Suitable ink compositions are described in US 5,984,467 and US 5,537,137.

Permanent substrate

The imaged ink receptor sheet of the present invention may be applied to many types of permanent substrates by use of the adhesive layer of the transfer element. Some permanent substrates include paper, polymer foils, metal, or card board.

Applications

The ink receptor sheet provided by the present invention may receive ink printed by conventional ink jet printers, such as thermal or bubble jet printers, piezoelectric printers, continuous flow printers, or valve jet printers. After the ink is printed on the ink receiving layer of the ink receptor sheet, the printed sheet is air dried.

Then a transfer element is contacted to the imaged ink receptor sheet. Typically, it is laminated with a conventional laminator, e.g. an EasySprint® Desktop laminator (E.I du Pont de Nemours & Company, Wilmington, DE). The temperature of the laminator rollers is usually at least about 80 °C, typically about 90 to about 130°C.

The temporary support of the transfer element is peeled off manually or automatically, whereby the adhesive layer of the transfer element is transferred to the imaged ink receptor sheet. The temporary support is peeled off preferably after cooling to room temperature. More typical is an additional hold time of 1-5 min.

The imaged ink receptor plus the adhesive layer from the transfer element are then contacted, typically laminated, like in the previous contact/lamination step to a permanent substrate. After this contact, typically lamination, the photopolymerizable layer of the ink receptor sheet and permanent substrate sandwich is overall exposed with actinic radiation through the temporary support of the ink receptor sheet for about 10 to about 30 sec. Some examples of suitable radiation sources are xenon lamps, mercury vapor lamps and carbon-arcs, laser fluorescent lamps with fluorescent materials emitting UV radiation and electronic flash devices.

Afterwards, the temporary support of the ink receptor sheet is easily peeled off to reveal the final ink jet image, encased between the adhesive and the ink receiving layers, and protected by the photopolymerized layer, on the permanent substrate. The temporary support of the ink receptor sheet is peeled off manually or automatically, typically after cooling to room temperature. More typical is an additional hold time of about 1 to about 5 min.

The overall exposure of the photopolymerizable layer of the ink receptor sheet can also be carried out before instead of after contacting, typically

laminating, the imaged ink receptor sheet plus the adhesive layer from the transfer element to the permanent substrate.

Furthermore, it is possible to contact, typically laminate, a photosensitive layer to the imaged ink receiving layer of the ink receptor sheet under the same process conditions as described above before a transfer element is applied. Suitable photosensitive materials are positive- and negative-working materials as those disclosed in US 3,649,268, US 4,174,216, US 4,892,802, and US 4,053,313. Typically, photosensitive materials are those of US 4,892,802.

This photosensitive layer is imagewise exposed with actinic radiation by using radiation sources like those previously described to produce tacky and non-tacky areas. The photosensitive layer may comprise a strippable base on its top which may be stripped before or after imagewise exposure. Suitable materials for such bases are synthetic resin films of polyethylene, polypropylene, polyamides, or polyesters. Then a toner is applied to the tacky areas of the imagewise exposed photosensitive layer. Powder toners as well as pigmented foils may be used. Such toner materials are disclosed in US 3,649,268; US 3,620,726; 3,909,282; and US 5,372,910 and US 5,427,894. These additional steps of applying a photosensitive layer, imagewise exposing it, and adding a toner may be repeated at least twice. Then the further steps of the transfer process according to the present invention are conducted as described above.

It is also possible to laminate an imaged ink receptor sheet of the present invention to an adhesive coated permanent substrate without transferring the imaged ink receptor sheet to a transfer element. All further process steps are conducted as described previously. The adhesive coated permanent substrate preferably comprises an adhesive layer like that of the transfer element. A transfer element of this invention may be laminated to any substrate to form this adhesive layer.

Industrial Utility

The ink receptor sheet, the ink jet printing system comprising the ink receptor sheet and a transfer element as well as the processes of the present invention have commercial utility for ink jet printing technologies, especially with aqueous ink dispersions. Pictorial as well as textured information may be printed. For multicolored images, yellow, cyan, magenta, and black inks may be used to advantage. Applications include desktop publishing, as well as wide format applications such as the printing of signs, banners, and the like. High quality images may be printed on a broad variety of substrates.

EXAMPLES

The following examples illustrate the invention, but do not limit it. Parts and percentages are by weight, unless otherwise stated. The average molecular weights of the polymers are given as weight average (Mw). Percent hydrolysis is given as mole percent hydrolysis of acetate groups on dry basis.

Example 1:

(I) Ink receptor sheet

Photopolymerizable layer

7 g of Elvanol® 52-22 (E.I du Pont de Nemours & Company, Wilmington, DE; polyvinyl alcohol, 87 – 89 % hydrolysis, viscosity of aqueous solution (4 % solids) at 20 °C by Hoppel falling ball method: 21-26 mPa s) were dissolved in 96.4 g water. 3.5 g Irgacure® 651 (benzil dimethyl ketal) were dissolved in 25.9 g TMPTMA (trimethylol propane trimethacrylate). This monomer/initiator solution was added to the Elvanol® solution and emulsified with a high speed mixer for 5 min. The emulsion was diluted with 150 g water and 67.2 g Plexol® D540 (Polymer Latex, Marl, Germany; aqueous dispersion of acrylic polymer based on methyl methacrylate and n-butyl acrylate, Brookfield viscosity 3-10 Pa s, 50 % of solids) were added and mixed under moderate stirring. The emulsion/dispersion was coated with a doctor knife onto a 125 µm thick untreated polyester base which formed the temporary support of the ink receptor sheet and dried at room temperature. The resulting coating weight was 60 mg/dm².

Ink receiving layer

3.6g Gantrez® S97 (ISPEurope, Guildford, GB; free acid of methyl vinyl ether/maleic anhydride copolymer, about Mw 2,200,000) were dissolved in 182.5 g water. 2.13 g Ludox® LS (E.I du Pont de Nemours & Company, Wilmington, DE; colloidal silica in water, 30 % of solids) were added and mixed. 2.8 g triethanolamine were added and mixed. 8.96 g Elvanol® 52-22 were added and stirred until dissolved. The final solution had a pH of 5.3 and a viscosity of 660 cP. The solution was coated with a Meyer bar onto the above mentioned photopolymerizable layer and dried at room temperature. The coating weight of the ink receiving layer was 80 mg/dm².

Transfer element

10.56 g Capa® 650 (Solvay Interlox, Warrington, GB; polycaprolactone Mw 50,000, melting range T_m 58 – 60 °C, glass transition temperature range T_g –60 to –70 °C) were dissolved in 80.1 g toluene and 8.9 g methanol. 0.44g Acematt® OK607 (Degussa Hüls; Germany; precipitated silica, 2 µm particle size) were

added and dispersed under vigorous stirring. The solution was coated with a doctor knife onto a 50 μm thick release treated polyester base which formed the temporary support of the transfer element and dried at room temperature to form an adhesive layer. The coating weight was 60 mg/dm^2 .

5 Process of use

A wrong reading 4 - color image was printed onto the ink receptor sheet with an AX-4 Digital Cromalin[®] ink jet printer (E.I du Pont de Nemours & Company, Wilmington, DE). A very uniform print with complete ink acceptance and no image disturbances or "beading" was achieved. Only slight surface tackiness was
10 observed directly after printing in areas where all 4 colors had been printed 100 % on top of each other. After 10 min. drying at room temperature the entire surface was found to be non-tacky.

The transfer element was laminated to the imaged ink receptor sheet with an EasySprint[®] Desktop laminator (E.I du Pont de Nemours & Company,
15 Wilmington, DE) at 115 °C roller temperature wherein the adhesive layer of the transfer element adhered to the imaged ink receiving layer. After cooling to room temperature and a 1 min. hold time the temporary support of the transfer element was peeled off without any residues. The adhesive layer of the transfer element was completely transferred to the printed ink receptor sheet without any adhesion
20 failure or edge lifting at the photopolymerizable layer/temporary support interface of the ink receptor sheet.

The ink receptor sheet plus the adhesive layer of the transfer element were laminated to a 120 g/m^2 Ikonorex[®] paper (Ikono Zanders, Germany) with an EasySprint[®] Desktop laminator at 115 °C roller temperature. After the
25 lamination the photopolymerizable layer was overall exposed through the temporary support of the ink receptor sheet for 15 sec in a commercial 1000 W UV exposure frame to render the photopolymerizable layer non-tacky. After the exposure the temporary support of the ink receptor sheet was easily peeled off without any damage of the surface or any adhesion failure between the layers or
30 to the paper substrate.

Example 2

Ink receptor sheet

Photopolymerizable layer

3.5 g Elvanol[®] 52-22 were dissolved in 46.8 g water. 1.75 g Irgacure[®] 651
35 were dissolved in 12.95 g TMPTMA. The monomer/initiator solution was emulsified in the Elvanol[®] solution as described in Example 1. The emulsion was diluted with 40 g water and 35 g Primal[®] CS-4000 (Röhm & Haas, Germany; aqueous dispersion of acrylic polymer, 48% of solids) was stirred in. The

emulsion/dispersion was coated with a doctor knife onto a 125 μm thick untreated polyester base which formed the temporary support of the ink receptor sheet and dried at room temperature. The coating weight was 60 mg/dm^2 .

Ink receiving layer

- 5 3.19 g Gantrez[®] AN119 (ISPEurope, Guildford, GB; methyl vinyl ether/maleic anhydride copolymer, Mw about 2,160,000) were dissolved in 133.5g water at 80 °C. 9.9g Elvanol[®] 52-22 were added and dissolved at 80 °C. After cooling to room temperature 3.05 g triethanolamine were added and mixed. The final solution had a pH of 5.8 and a viscosity of 380 cP. The solution was
10 coated onto the photopolymerizable layer and dried as described in example 1. The coating weight was 60 mg/dm^2 .

Process of use as described in Example 1

- After printing onto the ink receptor sheet, the surface was only slightly tacky over areas where all 4 colors had been printed 100% on top of each other. After
15 laminating the transfer element to the imaged ink receptor sheet and peeling the temporary support of the transfer element, the photopolymerizable layer was overall exposed. The imaged and exposed ink receptor sheet with the adhesive layer on top was then laminated to a 100 μm thick corona treated polyethylene foil. The temporary support of the ink receptor sheet was peeled off easily
20 without any damage of the surface or any adhesion failure between the layers or to the polyethylene foil.

Example 3

Ink receptor sheet

Photopolymerizable layer

- 25 12 g Elvacite[®] 2044 (E.I du Pont de Nemours & Company, Wilmington, DE; butyl methacrylate copolymer), 7 g TMPTA and 1 g Irgacure[®] 651 were dissolved in 80 g toluene. The solution was coated with a doctor knife onto a 125 μm thick untreated polyester base which formed the temporary support of the ink receptor sheet and dried at room temperature. The coating weight was 40 mg/dm^2 .

30 Ink receiving layer

- 3.19 g Gantrez[®] AN119 were dissolved in 133.5 g water at 80 °C. 9.9 g Moviol[®] 4-88 (Clariant GmbH, Germany; polyvinyl alcohol, 88 % hydrolysis, viscosity 4 mPa s) were added and dissolved at 80 °C. After cooling to room temperature 3.05 g triethanolamine were added and mixed. The final solution had
35 a pH of 5.4 and a viscosity of 140 cP. The solution was coated onto the photopolymerizable layer and dried as described in example 1. The coating weight was 80 mg/dm^2 .

Process of use as described in Example 1

After printing onto the ink receptor sheet, the surface was only slightly tacky over areas where all 4 colors had been printed 100 % on top of each other. After laminating the transfer element to the printed ink receptor sheet and peeling the temporary support of the transfer element, the imaged ink receptor sheet with the adhesive layer on top was laminated to a 200 μ thick aluminum foil. After the overall exposure of the photopolymerizable layer the temporary support of the ink receptor sheet was easily peeled off without any damage of the surface or any adhesion failure between the layers or to the aluminum foil.

Example 4

A wrong reading 4 - color image was printed as described in Example 1 onto an ink receptor sheet according to Example 1. Then a positive Cromalin® sheet (E.I du Pont de Nemours & Company, Wilmington, DE), after removal of its cover sheet, was laminated on top of the imaged ink receiving layer with an EasySprint® Desktop laminator (E.I du Pont de Nemours & Company, Wilmington, DE) at 115 °C roller temperature. This layer was imagewise exposed through its base to provide tacky and non-tacky areas. The base was peeled off, and a white powder toner was applied to the tacky areas to provide a background image for the ink jet image. The transfer element was then laminated to the imaged ink receptor sheet as described in Example 1 and the temporary support of the transfer element was peeled off without any residues. The adhesive layer of the transfer element was completely transferred to the printed ink receptor sheet without any adhesion failure or edge lifting at the photopolymerizable layer/temporary support interface of the ink receptor sheet.

The imaged ink receptor sheet plus the toned Cromalin® layer plus the adhesive layer of the transfer element were laminated to a clear polyester base with an EasySprint® Desktop laminator at 115 °C roller temperature. After the lamination the photopolymerizable layer was overall exposed through the temporary support of the ink receptor sheet for 15 sec in a commercial 1000 W UV exposure frame to render the photopolymerizable layer non-tacky. After the exposure the temporary support of the ink receptor sheet was easily peeled off without any damage of the surface or any adhesion failure between the layers or to the paper receptor.

Comparative Example 1

The solution for the ink receiving layer of Example 1 was directly coated onto a 125 μ m thick untreated polyester base which formed the temporary support of the ink receptor sheet as described in Example 1. The coating weight was 80 mg/dm².

A wrong reading 4 - color image was printed onto this ink receptor sheet as described in example 1 and basically the same results were obtained as described in Example 1.

5 The same transfer element as in Example 1 was laminated to the imaged ink receptor sheet with an EasySprint® Desktop laminator at 115 °C roller temperature. After cooling to room temperature and a 1 min hold time, an attempt was made to peel off the temporary support of the transfer element. However, because of the insufficient adhesion of the imaged ink receiving layer to the temporary support, the imaged ink receiving layer was transferred to the transfer
10 element. Because of this adhesion failure the printed image could not be transferred to a permanent substrate.

Comparative Example 2

The solution for the ink receiving layer of Example 1 was directly coated onto a 100 µm thick corona treated polyester base which formed the temporary support
15 of the ink receptor sheet as described in Example 1. The coating weight was 80 mg/dm².

A wrong reading 4 - color image was printed onto this ink receptor sheet as described in Example 1 and basically the same results were obtained as in Example 1.

20 The transfer element was laminated to the imaged ink receptor sheet with an EasySprint® Desktop laminator at 115 °C roller temperature. After cooling to room temperature and a 1 min. hold time, the temporary support of the transfer element was peeled off without any residues. The adhesive layer of the transfer element was completely transferred to the imaged ink receptor sheet without any
25 adhesion failure or edge lifting at the ink receiving layer/temporary support interface.

The ink receptor sheet plus the adhesive layer of the transfer element were laminated to a 120 g/m² Ikonorex® paper with an EasySprint® Desktop laminator at 115 °C roller temperature. After cooling to room temperature and a 1min. hold
30 time, the temporary support of the ink receptor sheet could barely be peeled off. The surface of the ink receiving layer was damaged and some areas of the printed image were pulled off with the temporary support. The final proof was unusable.

CLAIMS

What is claimed is:

1. An ink receptor sheet comprising, in order:
 - (a) a first temporary support, and
 - 5 (b) an ink receiving layer,
 - (c) characterized in that it further comprises a photopolymerizable layer between the first temporary support and the ink receiving layer.
2. The ink receptor sheet according to Claim 1, characterized in that the photopolymerizable layer in its non-photopolymerized state exhibits high adhesion to the ink receiving layer and the first temporary support, whereas in its photopolymerized state it exhibits high adhesion to the ink receiving layer and low adhesion to the first temporary support.
3. The ink receptor sheet according to Claims 1 – 2, characterized in that the photopolymerizable layer comprises at least one polymeric binder, at least one photopolymerizable, ethylenically unsaturated monomer, and at least one photoinitiator or photoinitiator system.
4. The ink receptor sheet according to Claims 1-3, characterized in that the photopolymerizable layer comprises at least one polymeric binder selected from the group consisting of polyvinylformal, polyvinyl butyral, polyvinyl alcohol, polyvinyl acetate, polyurethane esters, polyacrylates containing carboxylic groups, polymethacrylates, and copolymers of (meth)acrylic acid with (meth)acrylic esters, (meth)acrylic amides, vinyl compounds, styrene, and butadiene.
5. The ink receptor sheet according to Claims 1-4, characterized in that the photopolymerizable layer comprises at least one monomer selected from the group consisting of trimethylol propane trimethacrylate, bisacrylates or methacrylates of bisphenol A or its alkoxyated derivatives, and pentaerythritol tetraacrylate or methacrylate.
6. The ink receptor sheet according to Claims 1-5, characterized in that the ink receiving layer comprises at least one hydrophilic polymer.
7. The ink receptor sheet according to Claims 1-6, characterized in that the ink receiving layer comprises at least one polymer selected from the group consisting of homo- and copolymers of vinyl alcohol and/or pyrrolidone; homo- and copolymers of acrylic acid, methacrylic acid, and/or maleic acid and/or maleic acid anhydride, and/or their metal salts and/or their amine salts; gelatine, and starch.
8. An ink jet printing system comprising in combination:

- (I) an ink receptor sheet according to Claims 1-7 comprising in order:
- (1) a first temporary support,
 - (2) a photopolymerizable layer, and
 - (3) an ink receiving layer,
- and
- (II) a transfer element comprising:
- (III) a second temporary support, and
- (IV) an adhesive layer.
9. The ink jet printing system according to Claim 8, characterized in that the adhesive layer of the transfer element comprises at least one thermoplastic polymer.
10. The ink jet printing system according to Claims 8-9, characterized in that the adhesive layer of the transfer element comprises at least one polymer selected from the group consisting of acrylate and methacrylate copolymers, vinyl acetate copolymers, and polyamides.
11. The ink jet printing system according to Claims 8-10, characterized in that the adhesive layer of the transfer element comprises at least one crystalline polymer.
12. The ink jet printing system according to Claims 8-11, characterized in that the adhesive layer of the transfer element comprises at least one polycaprolactone.
13. A process for preparing an image on a permanent substrate comprising the steps of:
- (a) imagewise applying at least one ink image on an ink receptor sheet according to Claims 1-7, wherein the ink receptor sheet comprises, in order:
 - (1) a first temporary support,
 - (2) a photopolymerizable layer, and
 - (3) an ink receiving layer, and whereby the ink image is adjacent the ink receiving layer
 - (b) contacting the imaged ink receptor sheet with a transfer element according to Claims 8-12, comprising:
 - (I) a second temporary support, and
 - (II) an adhesive layer, whereby the ink image is adjacent the adhesive layer;
 - (c) removing the second temporary support to reveal the adhesive layer on top of the imaged ink receptor sheet,

(d) contacting the imaged ink receptor sheet with a permanent substrate, whereby the adhesive layer is adjacent the permanent substrate,

(e) overall exposing with actinic radiation the permanent substrate and imaged ink receptor sheet sandwich through the first temporary support, and

5 (f) removing the first temporary support to reveal the final image on the permanent substrate, wherein the image is encased between the ink receiving layer and the adhesive layer.

14. The process according to Claim 13, characterized in that contacting comprises laminating.

10 15. The process according to Claims 13-14, characterized in that the overall exposure of step (e) is carried out before instead of after step (d).

16. The process according to Claim 13-15, characterized in that it further comprises the following additional process steps, in order, between steps (a) and (b):

15 (g) laminating a photosensitive layer to the imaged ink receiving layer of the ink receptor sheet,

(h) imagewise exposing the photosensitive layer with actinic radiation to produce tacky and non-tacky areas, and

(i) applying a toner to the tacky areas.

20 17. The process according to Claim 16, characterized in that steps (g) to (i) are repeated at least once between steps (a) and (b).

18. The process according to Claims 16-17, characterized in that the photosensitive layer has a strippable base.

25 19. The process according to Claims 16-18, characterized in that the strippable base is removed before or after step (h).

20. The process according to Claims 16-19, characterized in that the photosensitive layer is a tacky, photopolymerizable layer.

30 21. The process according to Claims 16-20, characterized in that toner is selected from the group consisting of a pigmented toner powder and a pigmented foil in step (i).

22. A process for preparing an image on a permanent substrate comprising the steps of:

(a') imagewise applying at least one ink image on an ink receptor sheet according to Claims 1-7, wherein the ink receptor sheet comprises, in order:

35

(1) a first temporary support,

(2) a photopolymerizable layer, and

- (3) an ink receiving layer onto which the ink is imagewise applied,
- (b') contacting the imaged ink receptor sheet with a element comprising:
- 5 (I) a permanent support, and
- (II) an adhesive layer, whereby the ink image is adjacent the adhesive layer
- (c') overall exposing the imaged ink receptor sheet through the first temporary support with actinic radiation, and
- 10 (d') removing the first temporary support to reveal the final image on the permanent substrate.

23. The process according to Claim 22, characterized in that it further comprises the process, in order, between steps (a') and (b'):

- 15 (g') laminating a photosensitive layer to the imaged ink receiving layer of the ink receptor sheet,
- (h') imagewise exposing the photosensitive layer with actinic radiation to produce tacky and non-tacky areas, and
- (i') applying a toner to the tacky areas.

20 24. The process according to Claim 23, characterized in that steps (g') to (i') are repeated at least once between steps (a') and (b').

25. An imaged article comprising, in order:

- (1) a permanent substrate,
- (2) an adhesive layer,
- 25 (3) an ink image,
- (4) an ink receiving layer, and
- (5) a photopolymerized layer.

26. The imaged article according to Claim 25, characterized in that the ink image is formed by application of an ink jet ink.

30 27. The imaged article according to Claims 24-25, characterized in that it comprises at least one toned layer prepared according to Claims 16-21.

INTERNATIONAL SEARCH REPORT

In International Application No

PCT/US 01/14162

A. CLASSIFICATION OF SUBJECT MATTER
 IPC 7 B41M7/00 B41M5/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B41M

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 95 06564 A (REXHAM GRAPHICS INC) 9 March 1995 (1995-03-09) claim 1 figures	13-15, 22, 25, 26
X	US 5 766 398 A (CAHILL DOUGLAS ALLAN ET AL) 16 June 1998 (1998-06-16) claim 1 figures	13-15, 22, 25, 26
A	US 5 795 425 A (BRAULT DONALD ARMAND ET AL) 18 August 1998 (1998-08-18) the whole document	1-27
A	EP 0 782 931 A (DU PONT) 9 July 1997 (1997-07-09) the whole document	1-27
	-/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- *Z* document member of the same patent family

Date of the actual completion of the international search

10 August 2001

Date of mailing of the international search report

20/08/2001

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
 Fax (+31-70) 340-3016

Authorized officer

Martins Lopes, L

THIS PAGE BLANK (USPTO)